

MICROFABRICA®

MICROFABRICA®

MICA Freeform™

MATERIAL PROPERTIES



MICROFABRICA®

MATERIAL PROPERTIES

- Material Data Sheets...page 3
 - Palladium
 - Valloy-120™
- Material Comparison Tables...page 5
 - Palladium
 - Valloy-120™

MATERIALS DOSSIER



MICROFABRICA®

Palladium Materials Data Sheet

Composition

Palladium	99.99%	99.99%
-----------	--------	--------

Physical Properties

Crystal Structure	FCC	FCC	
Resistivity @ RT	14.9 μ ohm-cm	5.87	μ ohm-in
Density	12g/cc	0.43	lb/in ³
Thermal Conductivity (RT)	71W/m-K	494	BTU-in/hr-ft ²
CTE (RT)	11.76 μ m/m-°C	6.5	μ in/in-°F
Melting Point	1552°C	2826	°F

Mechanical Properties*

Yield Strength (0.2%)	1,100MPa	160	x 10 ³ psi
Young's Modulus	110GPa	16	x 10 ⁶ psi
Tensile Elongation	5%	5%	
Ultimate Tensile Strength	1,500MPa	220	x 10 ³ psi
Hardness	400HV	41	HRC
Poissons Ratio	0.39	0.39	

MICROFABRICA®

Valloy-120™ Materials Data Sheet

Composition

Nickel	80.00%	80.00%
Cobalt	20.00%	20.00%

Physical Properties

Crystal Structure	FCC	FCC
Resistivity @ RT	11.6μohm-cm	4.57μohm-in
Density	8.9g/cc	0.32lb/in ³
Thermal Conductivity (RT)	91W/m-K	631BTU-in/hr-ft ²
CTE (RT)	13.4μm/m-°C	7.4μin/in-°F
Melting Point	1726°C	3139°F

Mechanical Properties¹⁾

Yield Strength (0.2%)	900MPa	130x 10 ³ psi
Young's Modulus	170GPa	25x 10 ⁶ psi
Tensile Elongation	3%	3%
Ultimate Tensile Strength	1,100MPa	160x 10 ³ psi
Hardness	425HV	43HRC
Poissons Ratio	0.31	0.31

MICROFABRICA®

Palladium Materials Comparison Table

		as cast/drawn	Palladium (as fabricated)
UTS	MPa	896	1,500
Elongation		1-2%	5%
Hardness	HV (Vickers)	150-180	400
Modulus of Elasticity	GPa	200-215	110
Electrical Resistivity (@20C)	ohm - meters	2.50E-07	1.49E-07
CTE (0-100C)	/K	8.40E-06	1.18E-05

		Pt-10% Ir as cast/drawn	Microfabrica Palladium (as fabricated)
UTS	ksi	130	220
Elongation		1-2%	5%
Hardness	HV (Vickers)	150-180	400
Modulus of Elasticity	10 ⁶ psi	29-31.2	16
Electrical Resistivity (@68F)	ohm - in	9.84E-06	5.87E-06
CTE (32-212F)	/F	4.67E-06	6.56E-06

MICROFABRICA®

Valloy-120™ Materials Comparison Table

		Stainless Alloys			Microfabrica
		304 (half hard)	304 (Full hard)	17-4 H900	Valloy
UTS	MPa	1035	1275	1340	1,100
Yield .2%	MPa	760	965	1240	900
Elongation		10%	2-5%	7%	3%
Hardness	Rockwell C	30-32	40	44	43
Modulus of Elasticity	GPa	200	200	196	170
Electrical Resistivity (@20C)	ohm - meters	7.20E-07	7.20E-07	7.70E-07	1.16E-07
CTE (0-100C)	/K	1.66E-05	1.66E-05	1.08E-05	1.34E-05

		Stainless Alloys			Microfabrica
		304 (half hard)	304 (Full hard)	17-4 H900	Valloy
UTS	ksi	150	185	195	160
Yield .2%	ksi	110	140	180	130
Elongation		10%	2-5%	7%	3%
Hardness	Rockwell C	30-32	40	44	43
Modulus of Elasticity	10^6 psi	29	2900%	28	25
Electrical Resistivity (@68F)	ohm - in	2.84E-05	2.84E-05	3.03E-05	4.57E-06
CTE (32-212F)	/F	9.20E-06	9.20E-06	6.00E-06	7.44E-06

MICROFABRICA®

www.MICROFABRICA.com

